

Amendments to Specification

On page 8 of the specification, line 25 to the end of the page, Table 1, Example 4 is amended as follows:

Table 1

Example No.	Wt. %	MATRIX	Wt. %	RUBBER	Wt. %	Mineral Filler	Filler/ Rubber Ratio	Sample Average IZOD Ft-lb/in (J/m)	Standard Deviation Izod Ft-lb/in (J/m)
Control 1	90	B	10	C	0		0	9.5 (507)	0.4 (19)
2	85	B	10	C	5	A	0.5	9.1 (486)	0.5 (27)
3	80	B	10	C	10	A	1.0	10.4 (555)	0.7 (39)
4	85 75	B	10	C	15	A	1.5	4.5 (240)	2.7 (143)